

Capstock

## Solarkote® P-601 acrylic capstock

PROPERTIES	VALUE	UNITS	TEST METHOD
<b>Physical</b>			
Melt Flow Rate (230°C / 3.8 kg)	1.0	g / 10 min	ASTM D1238
Specific Gravity	1.16		ASTM D792
Water Absorption (24 hr. immersion)	0.4	% weight gain	ASTM D570
<b>Mechanical</b>			
Tensile Strength @ Maximum	3,400	PSI	ASTM D638
Tensile Elongation @ Break	90	%	"
Tensile Modulus	180,000	PSI	"
Flexural Strength, maximum (Yield)	4,800	PSI	ASTM D790
Flexural Modulus	170,000	PSI	ASTM D790
Notched Izod Impact(73°F/23°C)	1.4	ft-lb/in notch	ASTM D256
Rockwell Hardness	70	R	ASTM D785
<b>Thermal</b>			
HDT (1.82 MPa; annealed) <sup>1</sup>	136	°F	ASTM D648
Coefficient of Linear Thermal Expansion			ASTM E831
0°F	6.5	in/in/°F x 10 <sup>-5</sup>	"
20°F	6.9	in/in/°F x 10 <sup>-5</sup>	"
75°F	7.6	in/in/°F x 10 <sup>-5</sup>	"
100°F	8.3	in/in/°F x 10 <sup>-5</sup>	"
Taber Abrasion Resistance, 500g load, #cycles/unit			ASTM D1044
100	0.0010	lost weight	"
500	0.0105	lost weight	"
1000	0.0165	lost weight	"
2000	0.0355	lost weight	"
Vicat Softening Point (50°C/hr; 10N)	158	°F	ASTM D1525
Vicat Softening Point (50°C/hr; 50N)	140	°F	ASTM D1525
Thermal Conductivity	1.5	BTU/hr*ft <sup>2</sup> *F/in	ASTM C177
<b>Optical</b>			
Refractive Index (ND @ 73°F)	opaque		ASTM D542

Data given are average values and should not be used for specification purposes.

1. Annealing Cycle: 4hrs @ 80°C

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema Inc. expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OR MERCHANTABILITY, OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE  
See MSDS for Health & Safety Considerations.

Altuglas®, Plexiglas®, DR®, VOD® and Solarkote® are registered trademarks of Arkema.  
Plexiglas® and Solarkote® acrylic resins are combustible thermoplastics. Observe fire precautions appropriate for comparable forms of wood and paper. For building uses, check code approvals. Impact resistance is a factor of thickness. Avoid exposure to heat or aromatic solvents. Clean with soap and water. Avoid abrasives.  
© January 2009 Arkema Inc. All rights reserved.

**ALTUGLAS**  
INTERNATIONAL  
ARKEMA GROUP

Altuglas International  
2000 Market Street  
Philadelphia, PA 19103