

# PLEXIGLAS® SHEET: Sound Transmission

ACRYLIC SHEET

## Sound Transmission Characteristics

Plexiglas® sheet offers sound loss characteristics that are equal to or better than those of glass. Since Plexiglas® sheet is also more resistant to breakage, it can be used as a transparent sound barrier to reduce noise levels and increase safety at the same time. Tables 1, 2, and 3 show noise reduction values and STC ratings for Plexiglas® sheet and other construction materials.

**TABLE 1**  
**Noise Reduction Values for Plexiglas® Sheet**  
(Ten panels were 75 x 100 in)  
Approximate noise reduction-dB(A)  
sheet thickness (in)

Frequency Spectrum of Noise Source	0.118* (3mm)	0.236 (6mm)	0.472 (12mm)	0.944 (24mm)	Double Glazed**
Low Frequencies Pre-Dominant	15	21	26	30	34
Flat Frequency Spectrum	25	29	33	35	38
High Frequencies Predominant	28	31	34	36	40

\*Estimated from measurements of .236", .472", and .944 sheet.

\*\* 0.236" Plexiglas® sheet, air space, 0.177" Plexiglas sheet.

**TABLE 2**  
**Noise Ratings of Plexiglas® Sheet**

Construction Thickness	STC
Plexiglas® sheet (0.118")*	25
Plexiglas® sheet (0.236")	29
Plexiglas® sheet (0.472")	33
Plexiglas® sheet (0.944")	35
Plexiglas® sheet [(0.236") air space (0.177")]	38

\* Estimated from measurements of .236" .476", and .944" sheet.

800 523-7500

[plexiglas.com](http://plexiglas.com)

**ALTUGLAS**  
INTERNATIONAL  
ARKEMA GROUP

**PLEXIGLAS**®  
BY ARKEMA

# PLEXIGLAS® SHEET: Sound Transmission

ACRYLIC SHEET

**TABLE 3**  
**Comparison of Noise Reduction Characteristics of Plexiglas® Sheet With Other Materials**

Construction material thickness	Approximate dB(A) noise reduction*
Plexiglas® sheet (0.118")	25
Plexiglas® sheet (0.236")	29
Plexiglas® sheet (0.472")	33
Plexiglas® sheet (0.944")	35
Double glazed Plexiglas® sheet	38
Glass (1/8")	25
Glass (1/4")	27
Plywood (1")	26
Steel (1/8")	37
Sheet lead (1/16")	38
Wood stud partition	38

\* Noise reduction obtained in enclosures depends on the completeness of the enclosure, tightness of joints, etc. The above dB(A) noise reductions were obtained in a completely enclosed, tightly joined structure. These conditions are seldom achieved in the real world; however, even under more realistic conditions, the use of Plexiglas sheet barriers can reduce noise levels enough to protect against heavy damage. The main purpose of this table is to indicate the relative noise reduction capabilities of commonly used materials in terms of dB(A).

The statements, technical information and recommendations obtained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Altuglas International/Arkema expressly disclaims any and all liability. NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OR MERCHANTABILITY, OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein should be construed as an inducement to infringe any patent, and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See MSDS for Health & Safety Considerations. Altuglas® and Plexiglas® are registered trademarks of Arkema. ©2013 Arkema Inc. All rights reserved. Rev. 5/13

800 523-7500

[plexiglas.com](http://plexiglas.com)

**ALTUGLAS**  
INTERNATIONAL  
ARKEMA GROUP

**PLEXIGLAS**®  
BY ARKEMA