

# PLEXIGLAS® SHEET: Thermal Properties

ACRYLIC SHEET

## Thermal Properties

### PLEXIGLAS® SHEET: U-FACTORS

The amount of heat conducted through Plexiglas® glazing is slightly lower than for glass of the same thickness. The values tabulated below are U-factors for vertical (windows) and horizontal (skylights) Plexiglas® glazing. R-values = 1/U-value. U-values are largely unaffected by the color of Plexiglas® sheet.

**Table 1**  
**U-Factor for Vertical Windows (BTU/hr./sq.ft./°F)**

	Winter Heat Loss*	Summer Heat Gain **
	Sheet Thickness (in)	Sheet Thickness (in)
<b>Construction</b>	0.118, 0.177, 0.236, 0.354, 0.472	0.118, 0.177, 0.236, 0.354, 0.944
<b>Single-Glazed</b>	1.06, 1.01, 0.96, 0.88, 0.81	0.98, 0.93, 0.89, 0.82, 0.76
<b>Double-Glazed</b>		
<b>1/4" air space</b>	0.55, 0.52, 0.49, -, -	0.56, 0.53, 0.50, -, -
<b>Double-Glazed</b>		
<b>1/2" air space</b>	0.47 0.45 0.43 - -	0.50, 0.48, 0.45, -, -

\* 15 mph wind velocity.

\*7.5 mph wind velocity.

**Table 2**  
**U-Factor for Horizontal Panels (BTU/hr./sq.ft./°F)**

Description	Winter*	Summer**
<b>Plastic Bubbles</b>		
<b>Single-Walled</b>	1.15	0.8
<b>Double-Walled</b>	0.7	0.46

\*Values from ASHRAE Handbook of Fundamentals. Thickness not listed; assume 3/16".

\*\*Based on area of opening, not total surface area.

Computer programs are available to calculate the complicated balance of energies due to solar heat gain, heat transfer, daylight and electrical lighting.

Many of the national skylight firms offer this calculation service. In addition, a Skylight Energy Handbook or an IBM computer disc is available by writing: AAMA, 2700

River Road, Suite 118, Des Plaines, IL 60018; or by calling 847-303-5664.

Web Site - WWW.AAMANET.ORG

800 523-7500

plexiglas.com

**ALTUGLAS**  
INTERNATIONAL  
ARKEMA GROUP

**PLEXIGLAS**  
BY ARKEMA

# PLEXIGLAS® SHEET: Thermal Properties

## ACRYLIC SHEET

The statements, technical information and recommendations obtained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Altuglas International/Arkema expressly disclaims any and all liability. NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OR MERCHANTABILITY, OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein should be construed as an inducement to infringe any patent, and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See MSDS for Health & Safety Considerations. PLEXIGLAS® is a registered trademark of Arkema in the Americas. ©2013 Arkema Inc. All rights reserved. Rev. 5/13

800 523-7500

**ALTUGLAS**  
INTERNATIONAL  
ARKEMA GROUP

[plexiglas.com](http://plexiglas.com)

**PLEXIGLAS®**  
BY ARKEMA