

Resin

Plexiglas® MI-7E acrylic resin

| PROPERTIES | VALUE | UNITS | TEST METHOD |
|---|---------|------------------------------|-------------|
| Physical | | | |
| Melt Flow Rate (230°C / 3.8 kg) | 1.2 | g / 10 min | ASTM D1238 |
| Specific Gravity | 1.17 | | ASTM D792 |
| Mold Shrinkage | 0.3-0.6 | % | ASTM D955 |
| Water Absorption (24 hr. immersion) | 0.3 | % weight gain | ASTM D570 |
| Mechanical | | | |
| Tensile Strength @ Maximum | | PSI | ASTM D638 |
| Tensile Elongation @ Break | 35 | % | " |
| Tensile Modulus | 380,000 | PSI | " |
| Flexural Strength, maximum (Yield) | 11,5000 | PSI | ASTM D790 |
| Flexural Modulus | 340,000 | PSI | ASTM D790 |
| Notched Izod Impact(73°F/23°C) | 0.8 | ft-lb/in notch | ASTM D256 |
| Rockwell Hardness | 62 | M | ASTM D785 |
| Thermal | | | |
| HDT (0.455 MPa; annealed) ¹ | 201 | °F | ASTM D648 |
| HDT (1.82 MPa; annealed) ¹ | 190 | °F | ASTM D648 |
| Vicat Softening Point (50°C/hr; 10N) | 210 | °F | ASTM D1525 |
| Vicat Softening Point (50°C/hr; 50N) | 195 | °F | ASTM D1525 |
| Thermal Conductivity | 1.4 | BTU/hr*ft ² *F/in | ASTM C177 |
| Optical | | | |
| Refractive Index (ND @ 73°F) | 1.49 | | ASTM D542 |
| Luminous Transmittance (0.125"/3.2 mm.) | 92 | % | ASTM D1003 |
| Haze (0.125 in./3.2 mm.) | <2 | % | ASTM D1003 |
| | | | |
| ASTM Classification | | PMMA 0221V1 | ASTM D788 |

Data given are average values and should not be used for specification purposes.

1. Annealing Cycle: 4hrs @ 80°C

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema Inc. expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OR MERCHANTABILITY, OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE
See MSDS for Health & Safety Considerations.
DR®, VOD® and Solarkote® are registered trademarks of Arkema.

Plexiglas® is a registered trademark of Arkema in the Americas.
Plexiglas® and Solarkote® acrylic resins are combustible thermoplastics. Observe fire precautions appropriate for comparable forms of wood and paper. For building uses, check code approvals. Impact resistance is a factor of thickness. Avoid exposure to heat or aromatic solvents. Clean with soap and water. Avoid abrasives.
© January 2009 Arkema Inc. All rights reserved.

ALTUGLAS
INTERNATIONAL
ARKEMA GROUP

Altuglas International
2000 Market Street
Philadelphia, PA 19103