

Plexiglas® MI7T

Acrylic Resin Technical Data Sheet

PROPERTIES	VALUE	UNIT OF MEASURE	TEST METHOD
GENERAL CHARACTERISTICS			
Density	1.17	g/cm ³	ISO 1183
Water Absorption, 24H	0.3	% weight gain	ISO 62
Mold Shrinkage	0.3-0.6	%	ISO 294
RHEOLOGICAL PROPERTIES			
Melt Flow Rate	2.0	g/10 min	ISO 1133, 230°C/3.8kg
Melt Volume-flow Rate	2.1	cm ³ /10 min	ISO 1133, 230°C/3.8kg
MECHANICAL PROPERTIES			
Tensile Modulus	2500	MPa	ISO 527-2/1A/1
Tensile Strength @ Yield	60	MPa	ISO 527-2/1A/5
Tensile Strength @ Break	50	MPa	ISO 527-2/1A/5
Tensile Strength @ Yield	5	%	ISO 527-2/1A/5
Tensile Strength @ Break	35	%	ISO 527-2/1A/5
Flex Stress @ Conventional Deflection	70	MPa	ISO 178, Method A
Flexural Modulus	2400	MPa	ISO 178, Method A
Charpy Impact Resistance – Un-notched	40	kJ/m ²	ISO 179-1/1eU/23°C
Charpy Impact Resistance – Un-notched	24	kJ/m ²	ISO 179-1/1eU/-40°C
Charpy Impact Resistance – Notched	4	kJ/m ²	ISO 179-1/1eA/23°C
Charpy Impact Resistance – Notched	2	kJ/m ²	ISO 179-1/1eA/-40°C
Izod Impact Resistance – Notched	5.0	kJ/m ²	ISO 180
Rockwell Hardness	68	M-Scale	ISO 2039-2
THERMAL PROPERTIES			
Vicat Softening Point - 50N	102	°C	ISO 306/B50, 50N
HDT - 1.82 MPa	93	°C	ISO 75-2, Method A, 1.8 MPa
HDT - 0.45 MPa	98	°C	ISO 75-2, Method B, 0.45 MPa
OPTICAL			
Refractive Index	1.49	—	ISO 489, 23°C
Luminous Transmittance	91	%	ASTM D1003, 3.2mm
Haze	< 2	%	ASTM D1003, 3.2mm

Data given are average values and should not be used for specification purposes. Please consult Arkema's disclaimer regarding the use of Arkema's products on <http://www.arkema.com/en/products/product-safety/disclaimer/index.html>. See SDS for Health & Safety Considerations. Plexiglas® is a registered trademark of Arkema in the Americas. UL is a registered trademark of UL LLC. ©2021 Arkema Inc. All rights reserved.